

EVEREST GREEN 02 CI WR SRC



| DESCRIPTION | NORM EN ISO 20347:2012 | RESULT | REQUIREMENT | |
|---|--|--|----------------------------|--------|
| UPPER: Nubuk leather, water repellent treatment, | 5.4.3 Tear strength | 255 N | ≥120 N | |
| | 5.4.6 Water vapor permeability Coefficient | 5,1 mg/cm ² h | ≥ 0,8 mg/cm ² h | |
| | | 31,4 mg/cm ² | ≥ 15,0 mg/cm ² | |
| LINING (INTERNAL SOCK): Membrane, Breathable, abrasion resistance. | 5.5.1 Tear strength | 52 N | ≥ 15 N | |
| | 5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry) | No holes | 25.600 cycles | |
| | | No holes | 12.800 cycles | |
| | 5.5.3 Water vapor permeability Coefficient | 5,0 mg/cm ² h | ≥ 2,0 mg/cm ² | |
| 29,5 mg/cm ² | | ≥20,0 mg/cm ² | | |
| FOOTBED: Removable, cushioned, antistatic insole. | 5.7.4.2 Abrasion resistance(Wet) Abrasion resistance(Dry) | No holes | 25.600 cycles | |
| | | No holes | 12.800 cycles | |
| OUTSOLE: PU 2D, Antislip sole, SRC | 5.8.2 Tear strength | 8,3 kN/m | ≥ 8 kN/m | |
| | 5.8.3 Abrasion resistance | 85 mm ³ | ≤ 150 mm ³ | |
| | 5.8.4 Flexing resistance | 2,00 mm | ≤ 4,0 mm | |
| | 5.8.5 Hydrolysis | 3,00 mm | ≤ 6,0 mm | |
| | 6.4.2 Oils resistance | 1% | ≤ 12% | |
| | 5.11 Pressed ceramic tile floor on detergent resistance | Flat slip | 0,33 | ≥ 0,32 |
| | | Heel slip | 0,29 | ≥ 0,28 |
| | | Stainless steel plate on glycerin resistance | | |
| | Flat slip | 0,21 | ≥ 0,18 | |
| | Heel slip | 0,16 | ≥ 0,13 | |

SIZES: 35-48;
MONDOPOINT: 11