

exena.

JASPER S3 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: pigmented leather water repellent,	5.4.3 Tear strength	207 N	≥ 120 N
	5.4.6 Water vapor permeability Coefficient	1,2 mg/cm ² h 18,8 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.2 Tear strength	45 N	≥ 15 N
	5.5.3 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	51.200 cycles
	5.5.4 Water vapor permeability Coefficient	4,7 mg/cm ² h 40,5 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
COUNTER LINING: Breathable, abrasion resistance.	5.5.2 Tear strength	38 N	≥ 15 N
	5.5.3 Abrasion resistance (Wet)	No holes	25.600 cycles
	Abrasion resistance (Dry)	No holes	51.200 cycles
	5.5.4 Water vapor permeability Coefficient	7,8 mg/cm ² h 63,3 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
SAFETY TOE CAP: Non metallic, polycarbonate, 200J	5.3.2.6 Impact resistance	14,5 mm	≥ 14 mm
	5.3.2.7 Compression resistance	15 mm	≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed.	5.8.3 Penetration resistance	Passed	≥ 1100 N

exena.

FOOTBED: X-DRY, Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance (Dry) Abrasion resistance (Wet)	No holes No holes	25.600 cycles 12.800 cycles
OUTSOLE: PU 2D, Antislip sole SRC	5.8.2 Tear strength 5.8.3 Abrasion resistance 5.8.4 Flexing resistance 5.8.5 Hydrolysis 5.10 Antistaticity 6.4.2 Oils resistance 6.2.10 Slip resistance on ceramic with glycerin (tilted towards the heel of 7°) (tilted towards the tip of 7°) 5.3.5.2 Slip resistance on ceramic with cleaning agent (tilted towards the heel of 7°) (tilted towards the tip of 7°)	9,1 kN/m 63 mm ³ 2 mm 2,5 mm Dry: 2,39 x10 ⁸ Ω Wet: 7,56 x10 ⁷ Ω 8 % 0,44 0,29 0,18 0,13	≥ 8 kN/m ≤ 250 mm ³ ≤ 4,0 mm ≤ 6,0 mm tra 1,00x10 ⁵ Ω e 1,00x10 ⁹ Ω ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

SIZES: 35-48
